



常州隽隆复合材料有限公司

CHANGZHOU JLON COMPOSITE CO.,LTD

Han Yuan 2-607/608,New North District,Changzhou 213022,Jiangsu,China

Tel:86-519-89810829

Email:info@jloncomposite.com



Technical Data Sheet

Carbon Fiber Powder

Code	Specification							
		bulk density g/L	Strength GPa	Moisture%	Carbon content%	Volume resistivity Ω /cm ³	Coefficient of linear expansion 1/K	L/D ratio
CFP-50	50m	300-570	≥ 3.5	≤ 0.8	≥ 95	1.5×10^{-3}	-0.74×10^{-6}	2: 1-8:1
CFP-200	200m		≥ 3.5	≤ 0.8	≥ 95			
CFP-400	400m		≥ 3.5	≤ 0.8	≥ 95			
CFP-800	800m		≥ 3.5	≤ 0.8	≥ 95			
CFP-1500	1500m		≥ 3.5	≤ 0.8	≥ 95			